



Engineered Seal Products
5920 Dry Creek Ln NE
Cedar Rapids, IA 52402
www.espint.com

V8038

Revision: C

MATERIAL: FKM
COMPOUND: V8038
SPECIFICATION: ASTM D 2000 M2HK710 A1-10 B38 EF31 EO78 Z1 Z2
COLOR: BROWN
CERTIFICATIONS: FDA CFR 21 177.2600, 3A Sanitary Standard 18 Class I, EC 1935/2004, NSF 61
ADDITIONAL NOTES: -

Spec	<u>Original Physical and Mechanical Properties</u>	<u>Requirements</u>	<u>Result</u>
Z1	Hardness, Shore A Pts, ASTM D 2240	75±5	74
	Tensile Strength, MPa (psi) min., ASTM D 412	10.0 (1450)	11.5 (1667)
	Ultimate Elongation, % min., ASTM D 412	175	212
	Modulus @ 100%, MPa (psi), ASTM D 412	-	5.9 (859)
	Density, (Mg/m ³)	-	2.13
A1-10	<u>Heat Resistance (ASTM D 573) 70 h @ 250°C</u>	<u>Requirements</u>	<u>Result</u>
	Change in Hardness, Pts max.	10	4
	Change in Tensile, % max.	-25	-5
	Change in Elongation, % max.	-25	-24
	Change in Weight, % max.	-	-3
B38	<u>Compression Set (ASTM D 395, Method B) 22 h @ 200°C</u>	<u>Requirements</u>	<u>Result</u>
	% of Original Deflection, max.	50	14.2
EF31	<u>Fluid Resistance (ASTM D 471) 70 h in ASTM Fuel C @ 23°C</u>	<u>Requirements</u>	<u>Result</u>
	Change in Hardness, Pts	±5	-4
	Change in Tensile, % max.	-25	-16
	Change in Elongation, % max.	-20	-18
	Change in Volume, %	0~+10	4.2

Note: the values listed above are only valid for material samples prepared for laboratory test purposes as documented in the standards listed above



Engineered Seal Products
5920 Dry Creek Ln NE
Cedar Rapids, IA 52402
www.espint.com

V8038

Revision: C

	<u>Test Description</u>	<u>Requirements</u>	<u>Result</u>
EO78	<u>Fluid Resistance (ASTM D 471) 70 h in Liquid No. 101 @ 200°C</u>		
	Change in Hardness, Pts	-15~+5	-12
	Change in Tensile, % max.	-40	-25
	Change in Elongation, % max.	-20	-14
	Change in Volume, %	0~+15	14.1
Z2 (EO88)	<u>Fluid Resistance (ASTM D 471) 70 h in Fluid No. 2, Blend 7700 @ 200°C</u>		
	Change in Hardness, Pts	-15~+5	-13
	Change in Tensile, % max.	-40	-37
	Change in Elongation, % max.	-20	-18
	Change in Volume, % max.	25	24.3
C2.1.1	<u>Low Fat Tolerance Absorption (ASTM D 471) 22 h @ 70°C</u>		
	Change in Hardness, Pts	±6	-3
	Change in Tensile, %	-	-22
	Change in Elongation, %	-	8
	Change in Weight, %	±5	0.5
	Change in Volume, %	±5	0.1
	Change in Visual Appearance	-	Pass
C2.2.1	<u>Milk Fat Absorption (ASTM D 471) 22 h @ 70°C</u>		
	Change in Hardness, Pts	±5	-1
	Change in Tensile, %	-	-22
	Change in Elongation, %	-	7
	Change in Weight, %	±5	0.4
	Change in Volume, %	±5	0.4
	Change in Visual Appearance	-	Pass

Note: the values listed above are only valid for material samples prepared for laboratory test purposes as documented in the standards listed above



		<u>Requirements</u>	<u>Result</u>
C2.2.2	<u>Distilled Water Absorption (ASTM D 471) 22 h @ 70°C</u>		
	Change in Hardness, Pts	±5	-2
	Change in Tensile, %	-	-20
	Change in Elongation, %	-	7
	Change in Weight, %	±5	0.5
	Change in Volume, %	±5	0.5
	Change in Visual Appearance	-	Pass
C2.2.3	<u>Air Aging Stability (ASTM D 573) 166 h @ 100°C</u>		
	Change in Hardness, Pts	±10	-1
	Change in Tensile, %	-	10
	Change in Elongation, %	-	-17
	Change in Weight, %	-	0.1
	Change in Volume, %	-	0.1
	Change in Visual Appearance	-	Pass
D4.6	<u>Fluid Resistance (ASTM D 471) 22 h in Nitric Acid @ 82°C</u>		
	Change in Hardness, Pts	±5	-2
	Change in Tensile, %	-	-17
	Change in Elongation, %	-	14
	Change in Weight, %	±5	1.3
	Change in Volume, %	±5	2.4
	Change in Visual Appearance	-	Pass
D4.7	<u>Fluid Resistance (ASTM D 471) 22 h in Phosphoric Acid @ 82°C</u>		
	Change in Hardness, Pts	-	-1
	Change in Tensile, %	-	-21
	Change in Elongation, %	-	8
	Change in Weight, %	-	0.5
	Change in Volume, %	-	0.9
	Change in Visual Appearance	-	Pass

Note: the values listed above are only valid for material samples prepared for laboratory test purposes as documented in the standards listed above



Engineered Seal Products
5920 Dry Creek Ln NE
Cedar Rapids, IA 52402
www.espint.com

V8038

Revision: C

D4.8	<u>Fluid Resistance (ASTM D 471) 22 h in Alkaline Cleaner @ 82°C</u>	<u>Requirements</u>	<u>Result</u>
	Change in Hardness, Pts	±5	-2
	Change in Tensile, %	-	-23
	Change in Elongation, %	-	4
	Change in Weight, %	±5	0.5
	Change in Volume, %	±5	0
	Change in Visual Appearance	-	Pass
D4.9	<u>Fluid Resistance (ASTM D 471) 22 h in Chlorine Sanitizer @ 21°C</u>	<u>Requirements</u>	<u>Result</u>
	Change in Hardness, Pts	±5	-1
	Change in Tensile, %	-	-4
	Change in Elongation, %	-	1
	Change in Weight, %	±5	0.2
	Change in Volume, %	±5	-0.3
	Change in Visual Appearance	-	Pass

Note: the values listed above are only valid for material samples prepared for laboratory test purposes as documented in the standards listed above